Rev: 0
June 10, 2015

Fermilab
In-Process Weld Examination Form

Filled by engineer:

Project: PV2K Mod. Weld Type: Butt WPS #: SS-9-002

Drawing #: F10060997 Pipe #1 Size: 2-1/2" S5 Engineer: B. Hansen

Weld #: B Pipe #2 Size: 2-1/2" S5 Date: 10/13/16

Filled by inspector:

Welder: R. Mahoney Inspector: G. Johnson

WPQ Qualified? YES ☑ Other ☐

Filled by examiner in field:

Date: 10/13/16 Examiner: G. Johnson

In-Process Visual Examination (see more info on the next page)	***Check if OK***
a) joint preparation and cleanliness Joint surfaces are free of chips, particles, dust, rust, scale, oil, grease, etc.	✓
b) pre-heating: (N/A if ambient temperature ≥ 50° F [10° C]) ambient temp.____ pre-heat temp.____	N/A
c) AWS Filler Metal Specification A5.9 ER308L Manfacturer Harris Filler rod: Class 308L Diameter(s) 1/16 Is filler certified? Yes Is a copy of CMTR or COA available Yes Heat #(s) 38LHCL-56/T-2232 Lot#(s) gap -0- type of purge gas Argon purge flow-rate & duration 15 SCFH or O_2 reading < 1%	✓ ✓ ✓
c)(1) for butt welds: confirm ID at end preparation is within ± 1/32" and OD is aligned properly	✓
d) for brazing: position, flux, brazing temperature, wetting, and capillary action	N/A
e) for welding: condition of root pass (after cleaning) – external and/or internal	✓
e)(1) for SMAW (stick welding): slag removal and weld condition between passes	N/A
f) appearance of finished joint: No visible cracks, lack of fusion, porosity, obvious imperfections, incomplete penetration Filler material is fused to edges of parent material Depth of undercut (< 1/32", N/A if non-existent)____	✓ ✓ ✓

Best welding practices

a) Joint Preparation and Cleanliness:

Use scotch bright or Aluminum oxide to clean the joint. Use only wire brushes dedicated for stainless steel on stainless steel. Carbon steel brushes can leave carbon particles in the joint.

b) Preheating:

Minimum temperature for P1 (carbon steel) and P8 (304/316 stainless steel) is 50° F [10° C]. For all other materials or atypical stainless steels, refer to para. 330 of B31.3.

c) Variable specified by WPS (Welding Procedure Specification):

* Welding Machine:
  Remote foot pedal required
  DC straight machine required.
* Filler rod must be AWS A5.9 designation (for stainless)
* Record diameter and class (308SS or 304LSS ... etc.) of filler rod
* Required Filler Rod Class

If connecting	304SS to 304SS	use 308 filler rod
If connecting	304SS to 304LSS	use 308L filler rod
If connecting	304LSS to 304LSS	use 308L filler rod
If connecting	316SS or 304 SS to 316SS	use 316 filler rod

For any other combination consult with the Fermilab weld shop.

* CMTR--Certified Material Test Report, COA-Certificate of Analysis, COC-Certificate of Conformonce

* Purge Gas
  Purge gas must be 99.995% pure welding grade Argon. Boil off gas from a liquid argon dewar is acceptable.
* Purge Flow
  Purge gas must flow through the pipe, past weld joint to remove oxygen. As a general rule the pre-weld purge should give 5-6 volume changes.
* Oxygen concentration
  Oxygen concentration must be less than 1%. If available, use an oxygen monitor to measure the O2 concentration of the exhausting purge gas.
* Joint Clearance (gap)
  Butt weld: per WPS
* Socket weld: 1/16" (+1/16", -none) clearance between socket base and adjoining piece.
  End Preparation: Align inside surfaces of joint within ± 1/32" or WPS requirement (whichever is smaller). For unequal pipe diameters or thicknesses, refer to design drawing.
* Internal Alignment:
  Butt Weld: If the two pieces have the same OD and wall thickness, alignment can be confirmed using a straight edge on the OD.

(e) Inspection:

Repeat inspection after every pass (does not need a separate form)

Rev: 0
June 10, 2015

Fermilab
In-Process Weld Examination Form

Filled by engineer:

Project: PV2K Mod. | Weld Type: Butt | WPS #: SS-9-002

Drawing #: F10060997 | Pipe #1 Size: 2-1/2" | Engineer: M. White

Weld #: N | Pipe #2 Size: 2-1/2" | Date: 11/9/16

Filled by inspector:

Welder: D. Knight | Inspector: G. Johnson

WPQ Qualified? YES ☑ Other ☐

Filled by examiner in field:

Date: 11/9/16 | Examiner: G. Johnson

In-Process Visual Examination (see more info on the next page)	***Check if OK***
a) joint preparation and cleanliness Joint surfaces are free of chips, particles, dust, rust, scale, oil, grease, etc.	✓
b) pre-heating: (N/A if ambient temperature ≥ 50° F [10° C]) ambient temp.____ pre-heat temp.____	N/A
c) AWS Filler Metal Specification A5.9 308L Manfacturer Harris Filler rod: Class 308L Diameter(s) 1/16 Is filler certified? Yes Is a copy of CMTR or COA available Yes Heat #(s) 38LHCL-56/T-2238 ot#(s)	✓
gap ~0~ type of purge gas Argon	✓
purge flow-rate & duration____ or O_2 reading <1%	✓
c)(1) for butt welds: confirm ID at end preparation is within ± 1/32" and OD is aligned properly	✓
d) for brazing: position, flux, brazing temperature, wetting, and capillary action	N/A
e) for welding: condition of root pass (after cleaning) – external and/or internal	✓
e)(1) for SMAW (stick welding): slag removal and weld condition between passes	N/A
f) appearance of finished joint: No visible cracks, lack of fusion, porosity, obvious imperfections, incomplete penetration	✓
Filler material is fused to edges of parent material	✓
Depth of undercut (< 1/32", N/A if non-existent) N/A	

Best welding practices

a) Joint Preparation and Cleanliness:

Use scotch bright or Aluminum oxide to clean the joint. Use only wire brushes dedicated for stainless steel on stainless steel. Carbon steel brushes can leave carbon particles in the joint.

b) Preheating:

Minimum temperature for P1 (carbon steel) and P8 (304/316 stainless steel) is 50° F [10° C]. For all other materials or atypical stainless steels, refer to para. 330 of B31.3.

c) Variable specified by WPS (Welding Procedure Specification):

* Welding Machine:
  Remote foot pedal required
  DC straight machine required.
* Filler rod must be AWS A5.9 designation (for stainless)
* Record diameter and class (308SS or 304LSS ... etc.) of filler rod
* Required Filler Rod Class

If connecting	304SS to 304SS	use 308 filler rod
If connecting	304SS to 304LSS	use 308L filler rod
If connecting	304LSS to 304LSS	use 308L filler rod
If connecting	316SS or 304 SS to 316SS	use 316 filler rod

For any other combination consult with the Fermilab weld shop.

* CMTR--Certified Material Test Report, COA-Certificate of Analysis, COC-Certificate of Conformonce

* Purge Gas
  Purge gas must be 99.995% pure welding grade Argon. Boil off gas from a liquid argon dewar is acceptable.
* Purge Flow
  Purge gas must flow through the pipe, past weld joint to remove oxygen. As a general rule the pre-weld purge should give 5-6 volume changes.
* Oxygen concentration
  Oxygen concentration must be less than 1%. If available, use an oxygen monitor to measure the O2 concentration of the exhausting purge gas.
* Joint Clearance (gap)
  Butt weld: per WPS
* Socket weld: 1/16" (+1/16", -none) clearance between socket base and adjoining piece.
  End Preparation: Align inside surfaces of joint within ± 1/32" or WPS requirement (whichever is smaller). For unequal pipe diameters or thicknesses, refer to design drawing.
* Internal Alignment:
  Butt Weld: If the two pieces have the same OD and wall thickness, alignment can be confirmed using a straight edge on the OD.

(e) Inspection:

Repeat inspection after every pass (does not need a separate form)

AD/CRYOGENICS WELD MAPPING LIST	WELD MAP LIST NUMBER	REV
Reference Dwg. F100600997		

TITLE: Weldment, Pipe Run to PV2K

#	WELD #	DATE	WELDER ID	SIZE (in.)	TYPE	MATERIAL	RADIOGRAPHIC / IN-PROCESS INSPECTION
	A	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	B	10/13/16	Mahoney	2-½" SS	Butt	304/L	In-Process
	C	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	D	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	E	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	F	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	G	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	H	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	I	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	J	10/13/16	Mahoney	2-½" SS	Butt	304/L	
	K	11/2/16	Mahoney	2-½" SS	Butt	304/L	
	L	11/10/16	Mahoney	2-½" SS	Butt	304/L	
	M	11/9/16	D. Knight	2½" SS	Butt	304L	
	N	11/9/16	D. Knight	2-½" SS	Butt	321/304L	In-Process

AD/CRYOGENICS WELD MAPPING LIST **Reference Dwg.**	**WELD MAP LIST NUMBER**	**REV**
TITLE:		

#	WELD #	DATE	WELDER ID	SIZE (in.)	TYPE	MATERIAL	RADIOGRAPHIC / IN-PROCESS INSPECTION

WELDER ID	WELDER NAME	AFFILIATION	Prepared by: